

Type DS, DL, DP and DM insulation panels

Cement-bonded chipboard	Symbol	Test method	Unit	Value
Gross density	ρ_a		kg/m ³	1200
Thermal conductivity	λ_D	EN 13986, table 11	W/mK	0.230
Fire behaviour		EN 13501-1		A2-s1, d0
Bending strength		0743T027	N/mm ²	≥9.0
Bending elasticity modulus (not load-bearing)		0743T027	N/mm ²	≥4000
Tensile strength		0743T027	N/mm ²	≥0.5
Tensile strength per cycles		0743T027 0743T026	N/mm ²	≤0.3
Durability (swelling)		0743T026	%	Max. 1.5
Durability per cycles		0743T026	%	Max. 1.5
Structural properties – strength (elasticity modulus)		0743T027 EN 789/EN 1058	N/mm ²	≥4500
Sound absorption		EN 13986, table 10	250–500 Hz 1000–2000 Hz	0.10 0.30
Steam permeability		EN 13986, table 9	μ, damp μ, dry	30 50
Formaldehyde reduction		EN 13896, suppl. B	Class	E1

Expanded rigid polystyrene foam (EPS)	Symbol	Test method	Unit	Value
Gross density	ρ_a	SN EN 1602	kg/m ³	15
Thermal conductivity	λ_D	SIA V 279	W/mK	0.038
Fire behaviour		VKF	BKZ	5.1
Specific thermal capacity	C		Wh/kgK	0.39
Water vapour diffusion resistance factor	μ	SN EN 12086		40
Compression stress at 10% compression	σ_{10}	SN EN 826	kPa	≥60
Creep behaviour under pressure (50 years, compression <2%)	σ_c	SN EN 1606	kPa	≥12
Top application limit temperature, non-weight-bearing			°C	75
Cell content				Air

Expanded rigid polystyrene foam with graphite additive (EPS lambda)	Symbol	Test method	Unit	Value
Gross density	ρ_a		kg/m ³	20
Thermal conductivity	λ_D		W/mK	0.030
Fire behaviour		DIN 4102		B1
Compression stress at 10% compression			kPa	≥100
Compression stress at 2% compression			kPa	≥20–35
Heat distortion temperature, short-term			°C	95
Heat distortion temperature, long-term			°C	80–85
Water absorption after 28 days' underwater storage			Volume per cent	3–4
Water vapour diffusion resistance factor			μ	30–55

Intensely expanded rigid polystyrene foam (EPS perimeter)	Symbol	Test method	Unit	Value
Gross density	ρ_a	SN EN 1602	kg/m ³	≥30
Thermal conductivity	λ_D	SIA V 279	W/mK	0.033
Fire behaviour		VKF	BKZ	5.1
Specific thermal capacity	C		Wh/kgK	0.39
Water vapour diffusion resistance factor	μ	SN EN 12086		~70
Water absorption after long-term submersion	W _{lt}	SN EN 12087	%	≤3
Water absorption through diffusion	W _{dv}	SN EN 1288	%	≤3
Compression stress at 10% compression	σ_{10}	SN EN 826	kPa	≥250
Creep behaviour under pressure (50 years, compression <2%)	σ_c	SN EN 1606	kPa	≥60
Maximum installation depth (no pressing water)			m	6.0
Top application limit temperature, non-weight-bearing			°C	75
Cell content				Air

Rock wool	Symbol	Test method	Unit	Value
Gross density	ρ_a	EN 1602	kg/m ³	160
Thermal conductivity	λ_D	EN 12667	W/mK	0.045
Fire behaviour		EN 13501-1		A1
Compression stress at 10% compression	σ_{10}	EN 826	kPa	100
Tensile strength, vertical to panel board	σ_{ml}	EN 1607	kPa	25
Water absorption, short-term	W _p	EN 1609	kg/m ²	≤1
Water absorption, long-term	W _p	EN 12087	kg/m ²	≤3
Melting point		EN 4102-17	°C	>1000
Maximum application temperature			°C	250