

**Frame extension elements for wooden and wood-metal
lifting sliding doors Moisture-resistant and with sound insulation**

| Plywood | Symbol | Test method | Unit | Value |
|-----------------------------------|-------------|--------------|--------------------------|-------|
| Classification | | | | AW100 |
| Gross density | ρ_a | EN 323 | kg/m ³ | ~420 |
| Thermal conductivity | λ_D | | W/mK | 0.130 |
| Emission category | | UNI EN 717/2 | mg HCHO/m ² h | E1 |
| Bending strength (longitudinal) | | EN 310 | N/mm ² | 28 |
| Bending strength (lateral) | | EN 310 | N/mm ² | 32 |
| Elasticity modulus (longitudinal) | | EN 310 | N/mm ² | 3600 |
| Elasticity modulus (lateral) | | EN 310 | N/mm ² | 3800 |

| Glass wool | Symbol | Test method | Unit | Value |
|------------------------------|------------------------|----------------|-------------------|----------|
| Gross density | ρ_a | | kg/m ³ | ~22 |
| Thermal conductivity | λ_D | DIN EN 12667 | W/mK | 0.035 |
| Fire behaviour | | DIN EN 13501-1 | | 6q.3/A1 |
| Dimensional stability | | DIN 4108-10 | | DS (T1) |
| Water vapour diffusion | | DIN EN 12086 | | MU1 |
| Thickness tolerance category | | DIN EN 13162 | | T2 |
| Application temperature | | | °C | ≤250 |
| Airflow resistivity | kPa · s/m ² | DIN EN 29053 | | >5 (AF5) |

| Heavy bitumen foil | Symbol | Test method | Unit | Value |
|--------------------------------|----------|-------------|-------------------|-------|
| Gross density | ρ_a | | kg/m ³ | 10 |
| Maximum temperature resistance | | | °C | 160 |
| Resistance to cold | | | °C | -25 |

| Wood | Symbol | Test method | Unit | Value |
|----------------------|----------------|-------------|------|-------|
| Type | Spruce pine | | | |
| Certification | PEFC-certified | | | |
| Thermal conductivity | λ_D | | W/mK | 0.140 |