

Plinth elements for plastic lifting sliding doors

PVC Veka	Symbol	Test method	Unit	Value
Gross density	ρ_a	DIN EN ISO 1183	kg/m ³	1400–1460
Thermal conductivity	λ_D	DIN 52612	W/mK	0.160
Modulus of elasticity		ISO 527	MPa	3000
Impact resistance		ISO 179/1eU	kJ/m ²	Without break
Notch impact resistance		ISO 179/1eA	kJ/m ²	9.0
Tensile strength		ISO 527	MPa	52
Bending strength		ISO 178	MPa	77.8
Shore hardness D		ISO 868		81
Surface resistance		DIN IEC 60167	ROE [Ω]	>2.00E+14
Contact resistance		DIN IEC 60093	RD [Ω cm]	1.74E+16
Dielectric strength		DIN IEC 243	[kV/mm]	16.8
Dielectric constant ϵ_r		DIN 53483		3.0–3.6
Expansion coefficient		DIN 53752	[10 ⁴ /K]	7 · 10 ⁻⁵
Compressive strength		DIN 53421	N/mm ²	70
Vicat softening point		ISO 306 (B 50)	°C	72
Heat distortion temperature		ISO 75-2 (1.8 MPa)	°C	60
Water absorption		ISO 62 (after 216 hrs)	%	0.1

Plywood	Symbol	Test method	Unit	Value
Gross density	ρ_a	EN 323	kg/m ³	~420
Thermal conductivity	λ_D		W/mK	0.130
Emission category		UNI EN 717/2	mg HCHO/m ² h	E1
Bending strength (longitudinal)		EN 310	N/mm ²	25
Bending strength (lateral)		EN 310	N/mm ²	26
Elasticity modulus (longitudinal)		EN 310	N/mm ²	3100
Elasticity modulus (lateral)		EN 310	N/mm ²	3800

Intensely expanded rigid polystyrene foam (EPS perimeter)	Symbol	Test method	Unit	Value
Gross density	ρ_a	1602	kg/m ³	30
Thermal conductivity	λ_D	279	W/(m·K)	0.033
Specific thermal capacity	c		Wh/(kg·K)	0.39
Water vapour diffusion resistance factor	μ	12086		70
Thermal length expansion coefficient			K ⁻¹	5-7·10 ⁻⁵
Water absorption after long-term submersion	W_{It}	12087	%	≥ 3
Water absorption through diffusion	W_{dV}	12088	%	≥ 5
Fire behaviour classification in acc. with EN		13501-1		E
Fire behaviour group		VKF		RF3 (cr)
Compression stress at 10% compression	σ_{10}	826	kPa ²⁾	≥ 150
Top application limit temperature, non-weight-bearing			°C	75
Cell content				Air